

Isola Roofing Shingles

Roofing for pitched roofs down to 15° pitch

Description :

Isola Roofing Shingle is an asphalt roofing coating made with a fibreglass core saturated with polymer-modified bitumen. The underside is sprinkled with water-repellent sand, and the upper side is covered with slate grit. An advanced adhesive system in the sprinkled surface means that adhesion is immediate. The upper part of the back is coated with plastic foil that provides an antifriction layer and prevents adhesion in the package and to the substrate.



Application :

Ideal for use on cold and ventilated roof constructions, down to a 15° pitch. Iso-D Xtra underlay should be used for pitches between 15° and 18°. In areas particularly exposed to severe weather, Isola Isokraft should be used. Isola Roofing Shingles can, under certain conditions, be laid new-on-old on pitches above 19°; for more information, see the installation instructions.

Storage :

Produktet lagres på et jevnt underlag og bør ikke utsettes for direkte sollys. Paller må ikke settes ovenpå hverandre

Installation :

Install on a solid base – tongue and groove, OSB boards, plywood or similar. The foil on the back should not be torn off. At temperatures below +5 °C, the adhesive fields must be preheated. Due to subtle colour changes, roofing shingles from the same production series must be used.

For more details see laying instruction on our website.

Approvals and guarantee



Isola Roofing Shingles

Product data	Value	Designation
Content per. package	2,53 m ²	-
Thickness	3	mm
Construction height	115	mm
Surface	Slate granules	-
Width	1000	mm
Units (per m ²)	8,69	stk
Coverage area	0,115	m ²
Material	Glassfiberstamme mettet med polymermodifisert bitumen	-
Min roof angle	15	°
Weight pr. m ²	8850	g

Product number
506024
506001
506013

Properties	Method	Unit	Value
Resistance against heavy rain	-	Pa	350
Resistance to UV	-	-	Approved
Dimensional variation (mm)	EN 544	-	± 3
External fire performance according to EN 13501-5	CEN/TS 1187-2	-	Broof (t1), Broof (t2), Broof (t3)
Tensile strength MD	EN-544	N/50 mm	890 ± 200
Tensile strength CMD	EN-544	N/50 mm	690 ± 200
Tear resistance CMD	EN-544	N	120 ± 20
Durability of mechanical resistance	EN 1297	-	Pass
Adhesive of the protective finishing	EN-544	g	< 1,2
Flow resistance at elevated temperature after artificial ageing	EN-544	mm at 90 °C	< 2
Water absorption	EN-544	%	< 1
Water permeability/Content of bitumen	EN-544	g/m ²	1300
Dangerous Substances	No method available	-	None

